

Acetal

Material Tolerance



Acetal Natural/Black Rod

Nominal Diameter	Tolerance in mm
4	+0.10 to +0.30
5 - 6	+0.10 to +0.60
8 - 10	+0.10 to +0.70
12 - 16 - 18 - 20	+0.20 to +0.80
22 - 25 - 28 - 30	+0.20 to +1.00
32 - 36 - 40	+0.20 to +1.20
45 - 50 - 56	+0.30 to +1.30
60 - 65 - 70	+0.30 to +1.60
75 - 80	+0.40 to +2.00
85 - 90	+0.50 to +2.20
100	+0.60 to +2.50
110	+0.70 to +3.00
120	+0.80 to +3.50
130 - 140	+0.90 to +3.80
150	+1.00 to +4.20
165 - 180	+1.20 to +5.00
200	+1.30 to +5.50
230 - 250	+1.50 to +6.20
300	+1.50 to +7.50

Acetal Natural/Black Sheet

Nominal Thickness	Tolerance in mm
1	-0.10 to +0.10
2	-0.15 to +0.15
3 - 4	-0.20 to +0.20
5 - 6	-0.25 to +0.25
8 - 10	+0.20 to +1.10
12 - 16 - 20 - 25	+0.30 to +1.50
30 - 35 - 40 - 45 - 50	+0.50 to +2.50
60	+0.50 to +3.50

Direct Plastics Ltd. Rother Valley Way, Holbrook, Sheffield, S20 3RW

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples.

We reserve the right of technical alterations.