



# Acetal Black

POM-C (Polyacetal - Copolymer)

Colour: Black

Density: 1.41g/cm<sup>3</sup>

## Material Data Sheet

Mechanical Properties	Parameter	Value	Unit	DIN/EN/ISO
Modulus of elasticity (tensile test)	1mm/min	2800	MPa	527-2
Tensile strength	50mm/min	67	MPa	527-2
Tensile strength at yield	50mm/min	67	MPa	527-2
Elongation at Yield	50mm/min	9	%	527-2
Elongation at break	50mm/min	32	%	527-2
Flexural strength	2mm/min 10N	91	MPa	178
Modulus of elasticity (flexural test)	2mm/min 10N	2600	MPa	178
Compression Strength	1%/2% 5mm/min 10N	20/35	MPa	604
Compression modulus	5mm/min 10N	2300	MPa	604
Impact strength (Charpy)	Max. 7,5J	150	kJ/m <sup>2</sup>	179-1eU
Notched impact strength (Charpy)	Max. 7,5J	6	kJ/m <sup>2</sup>	179-1eA
Ball indentation hardness	-	165	MPa	2039-1

Thermal Properties	Parameter	Value	Unit	DIN/EN/ISO
Glass transition temperature	-	-60	°C	53765
Melting temperature	-	166	°C	53765
Service temperature	Short term	140	°C	-
Service temperature	Long term	100	°C	-
Thermal expansion (CLTE)	23-60°C, Long	13	10 <sup>-5</sup> K <sup>-1</sup>	11359-1;2
Thermal expansion (CLTE)	23-100°C, Long	14	10 <sup>-5</sup> K <sup>-1</sup>	11359-1;2
Specific heat	-	1.4	J/(g*K)	22007-4:2008
Thermal conductivity	-	0.39	W/(K*m)	22007-4:2008

Electrical properties	Parameter	Value	Unit	DIN/IEC
Surface resistance	-	>10 <sup>12</sup>	Ω	60093

Other properties	Parameter	Value	Unit	DIN/EN/ISO/IEC
Water absorption	24h/96h (23°C)	0.05/0.1	%	62
Resistance to hot water/bases	-	(+)	-	-
Resistance to weathering	-	(+)	-	-
Flammability (UL94)	Corresponding to	HB	-	60695-11-10

Direct Plastics Ltd. Rother Valley Way, Holbrook, Sheffield, S20 3RW

The following information corresponds with our current knowledge and indicates our products and possible applications. We cannot give a legally binding guarantee of certain properties or the suitability for a specific application. Existing commercial patents must be observed. A definitive quality guarantee is given in our general conditions of sales. Unless otherwise stated, these values represent averages taken from injection moulding samples.

We reserve the right of technical alterations.